

B. Amendment to the Claims

The following is a complete listing of the claims, and replaces all earlier versions and listings.

1. (Withdrawn) A molding method for a foamed product, characterized in that a chip- or pellet-like resin material is evacuated and subjected to dehumidifying/drying processing, and replacement processing in an inert gas in a pre-processing unit, the resin material is then held in an inert gas of a predetermined temperature and pressure in an inert gas permeation unit for a predetermined period of time, the temperature and pressure are decreased, the material is fed to a material hopper whose temperature and pressure are controlled, the material is fed to a plasticizing unit to which a gas of a predetermined temperature and pressure is fed, the resin material is melted in the plasticizing unit, the resin material is injected/charged into a mold which is evacuated in advance to a pressure not more than atmospheric pressure, the pressure is restored to atmospheric pressure after the resin material is cooled for a predetermined period of time, and a foamed product is extracted by opening the mold.

2. (Withdrawn) The method according to claim 1, characterized in that the dehumidifying/drying processing in the pre-processing unit is performed by using hot air passing through a moisture adsorbing material such as silica gel.

3. (Withdrawn) The method according to claim 1, characterized in that in the dehumidifying/drying processing in the pre-processing step, evacuation is performed by a vacuum pump first, and then replacement is performed by using an inert gas.

4. (Withdrawn) The method according to claim 1, characterized in that evacuation is performed by using a vacuum pump after the pre-processing step is performed by using hot air passing through a moisture adsorbing material such as silica gel, and replacement is then performed by using an inert gas.

5. (Withdrawn) The method according to claim 1, characterized in that when the inert gas permeates the resin, the temperature is not more than a thermal deformation temperature of the resin, and the resin is in a solid state.

6. (Withdrawn) The method according to claim 1, characterized in that when the inert gas permeates the resin, the pressure of the gas falls within a range of 0.5 MPa to 6 MPa.

7. (Withdrawn) A foam molding method characterized in that while a material is fed from the inert gas permeation unit, an opening/closing valve of a material hopper which is located on the plasticizing unit side is kept closed.

8. (Withdrawn) The method according to claim 1, characterized in that while a material is fed from a material hopper to the plasticizing unit, an opening/closing valve of the material hopper which is located on the inert gas permeation unit side is kept closed.

9. (Withdrawn) The method according to claim 1, characterized in that a metering portion of a molding apparatus is filled with an inert gas of a pressure of 0.1 MPa to 6 MPa and a temperature not more than a thermal deformation temperature of the material by an inert gas feed controller.

10. (Withdrawn) The method according to claim 1, characterized in that the plasticizing step in a molding apparatus is performed with a back pressure of 0.5 MPa to 6 MPa.

11. (Withdrawn) The method according to claim 1, characterized in that a resin discharge port of the plasticizing unit of a molding apparatus can be opened/closed by an opening/closing needle, and is kept closed except when a resin material is discharged and the holding pressure step is performed.

12. (Withdrawn) The method according to claim 1, characterized in that the mold incorporates a valve gate type hot runner system, and a valve gate is kept closed except when a resin material is discharged and the holding pressure step is performed.

13. (Withdrawn) A molding apparatus for a foamed product, characterized by comprising a preprocessing unit which is connected to a material silo and removes moisture and fats adhering to a material, an inert gas permeation unit which is connected to said pre-processing unit and constituted by an inert gas cylinder, a pressure reducing unit, a pressure-relief valve, a gas metering unit, gas flowmeter, a heater, a

pressure sensor, a pressure controller, a temperature sensor, a temperature controller, and a pressure vessel, a material feed pump connected to said gas permeation unit, a material hopper connected to said material feed pump, an opening/closing valve controller connected to said inert gas permeation unit and an opening/closing valve of said material hopper, a gas feed controller coupled to a metering portion of a molding unit plasticizing unit through a gas feed pipe, a molding unit, and a mold which is connected to a vacuum pump and has a seal member.

14. (Withdrawn) The apparatus according to claim 13, characterized in that said pre-processing unit comprises a dehumidifier and an inert gas feed unit.

15. (Withdrawn) The apparatus according to claim 13, characterized in that said material hopper has two opening/closing valves and comprises a heater, a temperature sensor, a temperature adjusting unit, a pressure sensor, a pressure controller, a fan, and a fan motor.

16. (Withdrawn) The apparatus according to claim 13, characterized in that said gas feed controller comprises an inert gas cylinder, a pressure reducing valve, a pressure-relief valve, a gas metering unit, a gas flowmeter, a heater, a pressure sensor, a pressure controller, a temperature sensor, a temperature controller, and a pressure vessel.

17. (Withdrawn) A foamed product characterized by being molded by the molding method defined in claim 1.

18. (Withdrawn) A foamed product characterized by being molded by the molding apparatus defined in claim 13.

19. (Withdrawn) A foam molding method of molding a resin molded member by injecting a resin material into a mold, characterized in that a foaming gas is made to permeate the resin material in the step before the step of plasticizing the resin material.

20. (Withdrawn) A foam molding method of molding a resin molded member by injecting a resin material into a mold, characterized in that after the step of dehumidifying/drying the resin material, the step of making an inert gas permeate the resin material, and then the resin material is injected into a mold through the plasticizing step.

21. (Withdrawn) A molding method for a foamed product, characterized in that a chip- or pellet-like resin material is dehumidified and evacuated/dried, an atmosphere is replaced by an inert gas such as nitrogen or carbon dioxide gas, and then the resin material is held for a predetermined period of time at a temperature not more than a thermal deformation temperature of the resin material and a pressure of 0.5 to 0.6 MPa which is not more than a supercritical pressure of the inert gas to make the inert gas permeate the resin material.

22. (Withdrawn) A foamed product characterized by formed by the method defined in claim 21 with an average cell diameter of 10 μm to 60 μm and a foaming ratio of 5 to 20%.

23-35. (Cancelled)

36. (Withdrawn) A manufacturing method for a structural member molded from a resin material, characterized in that a mold member having a cavity corresponding to the structure to be molded, injection means for injecting the molten resin material into the mold member, means for injecting a gas into the molten resin material in the cavity, and means for controlling a surface temperature of the mold member are provided, and the surface temperature of the mold is controlled to a temperature not more than a predetermined temperature with respect to a thermal deformation temperature of the resin material by the control means to make bubbles of the gas near a surface position in a resin molded product become smaller than bubbles of the gas at a central portion of the molded product.

37-39. (Cancelled)

40. (Withdrawn) A screw fastening member characterized in that the screw fastening member has a screw hole with which a male thread is threadably engaged, and is molded from a resin material, and cells having diameters on the micron order are

formed in the molded product by injecting a gas into the resin material in the step of processing the resin material.

41. (Withdrawn) A processing method for an antivibration member, characterized in that a pellet-like resin material fed to a resin material portion is fed to a hopper connected to a plasticizing unit of an injection molding unit, the resin material is fed from the hopper to a plasticizing portion of the plasticizing unit, the resin material is heated and kneaded by rotation of a screw mounted in the plasticizing unit and heat generated by a heater, a gas is fed from a gas feed portion to the plasticizing portion through a feed path, the molten resin material and the gas are mixed and the gas permeates the resin material in the plasticizing portion, a predetermined amount of mixture of the resin material and the gas is charged into a cavity in a mold whose temperature is controlled to a predetermined temperature in advance at a predetermined pressure and speed, and the holding pressure step is performed for a predetermined period of time with a predetermined holding pressure, thereby obtaining a molded product after cooling.

42. (Currently Amended) ~~A molded product which is made of a resin material and on which~~ An anti-vibration device comprising:

first means including a vibration source object; ~~[[and]]~~

second means including a reception object for receiving a signal from the vibration source object; ~~and are mounted, characterized in that damping function objects for damping vibrations generated by the vibration source object are contained in the molded product in the molding step for the molded product~~

a molded product comprising gas-cells having a size from 10 to 100 μm ,
wherein the first means and the second means are arranged on the molded
product,
wherein a damping factor of the molded product between the first means
and the second means is not less than 35 dB/sec, and
wherein a flexural rigidity of the molded product is from 4,500 to 9,800
Mpa.

43. (Currently Amended) The ~~molded product~~ anti-vibration device according to claim 42, ~~characterized in that~~ wherein the vibration source object comprises a rotating member.

44. (Currently Amended) The ~~molded product~~ anti-vibration device according to claim 42, ~~characterized in that~~ wherein the reception object comprises an optical element.

45. (Currently Amended) The ~~molded product~~ anti-vibration device according to claim 42, ~~characterized in that~~ wherein the molded product comprises a housing in which the object incorporated in electric equipment is mounted.

46-53. (Cancelled)

54. (Withdrawal) A manufacturing method for a damping function molded product, characterized in that injection molding is performed by using resin pellets which an inert gas of not more than a supercritical pressure is made to permeate in advance at a temperature not more than a thermal deformation temperature of a resin material.

55. (Withdrawal) The method according to claim 54, characterized in that a mixture of the resin material and the inert gas controls the number, shapes, and sizes of cells in the molded product by controlling conditions including a pressure with which the gas is injected into the resin material, an amount of gas injected, an injection pressure of the resin material, an injection speed, an injection amount, a holding pressure, a holding pressure time, a cooling gradient of the mold, and a cooling time.

56. (New) A method of manufacturing an anti-vibration device, which dampens a vibration between a first means including a vibration source object and a second means including a reception object for receiving a signal from the vibration source object, the method comprising the steps of:

 saturating a resin material with an inert gas by adjusting a pressure and an amount of the inert gas;

 molding a molded product in which a number, shapes and sizes of gas-cells are adjusted by controlling an injection pressure, an injection speed, an injection amount, a holding pressure, a cooling gradient of a mold, and a cooling time and injecting the resin material into the mold; and

 mounting the first means and the second means to the molded product.

57. (New) The method according to claim 56, wherein the vibration source object comprises a rotating member.

58. (New) The method according to claim 56, wherein the reception object comprises an optical element.

59. (New) The method according to claim 56, wherein the molded product comprises a housing in which the object incorporated in electric equipment is mounted.

60. (New) The method according to claim 56, wherein injection molding is performed by using resin pellets, wherein an inert gas of not more than a supercritical pressure is permeated in advance at a temperature not more than a thermal deformation temperature of the resin material.